



NARKRAFT REINFORCED 490

INFORMATIVE
DATA SHEET



PAPER PACK

STRUCTURE

BACKING: glass fiber reinforced kraft paper
ADHESIVE: synthetic rubber / hydrocarbonic resins
CORE: recycled paper and paperboard.


SUITABLE FOR

Heavy packaging; the stiffness of the backing permits an easy application also without hand dispensers

AVAILABLE COLOURS

Brown

Self adhesive tape with siliconized fiberglass reinforced kraft paper backing. The high performance hot melt adhesive and the reinforced backing makes this product the ideal choice for the heaviest packaging needs. The particular adhesive formulation ensures an excellent tack on the cartons with consequent tamper evident characteristics. The stiffness of the backing permits the application also without hand dispensers.



BACKING WEIGHT
105 g/m²



BREAKING LOAD
> 66 Kg/5cm



HEAVY WEIGHT PACKAGING















ORGANIC SOLVENTS FREE



PAPER PACK TAPES

INFORMATIVE
DATA SHEET



	 backing weight g/m ²	 total thickness µm	 adhesion N/cm	 breaking load Kg/5cm	 elongation at break %	 available colours	 heavy weight packaging	 medium weight packaging	 light weight packaging	 automatic sealing machine	 easy cut	 FSC FSC® C135011 on request
ECOMASK® 460	58	135	> 2,2	> 15	> 7	● ○			•	•	•	•
ECOMASK® HM 430	55	120	> 3,2	> 14	> 8	●			•	•	•	•
RENEWA® TAPE 465	58	135	> 2,2	> 15	> 7	● ○			•	•	•	•
NARKRAFT REINFORCED 490	105	200	n. r.	> 66	> 5	●	•			•		
ECOMASK® REINFORCED 460	58	190	> 2,2	> 20	> 5	●		•		•		•

● brown ○ white

Updated on 11/2023



NAR S.P.A.
Legnaro (PADOVA) ITALY
www.nar-spa.com

It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product suitability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.



www.nar-spa.com/technical-notes.html