NARMASK HM 320

INFORMATIVE DATA SHEET

HM MASKING

COMPOSITION

BACKING: lightly crepe paper ADHESIVE: synthetic rubber / hydrocarbonic resins CORE: recycled paper and paperboard

UITABLE FOR

Light weight fixing; DIY

VAILABLE COLOUR

White

The tape has high conformability, good mechanical resistance and it cuts easily. Practical and economical, it is used for general purpose applications in DIY sector.



BACKING WEIGHT 52 g/m²



ADHESION > **2,7 N/cm**



BREAKING LOAD



ORGANIC SOLVENTS FREE

D.I.Y.

K EASY CUT

NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com





DNV





INFORMATIVE DATA SHEET

			\sim	iiin			X	Tí	*
	backing weight g/m²	total thickness μm	adhesion N/cm	breaking load N/cm	elongation at break %	available colours	organic solvents free	D.I.Y.	easy cut
NARMASK HM 320	52	115	> 2,7	> 25	> 6	0	•	•	•
NARMASK HM 330	55	120	> 3,6	> 27	> 8	0 •	•	•	•

⊖ white

yellow



NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product vitability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.



www.nar-spa.com/ technical-notes.html