

PRINTED TAPES

COMPOSITION

BACKING: printed biaxially oriented polypropylene film ADHESIVE: natural rubber / hydrocarbonic resins / solvent CORE: recycled paper and paperboard

SUITABLE FOR

Documents protection on parcels during shipments

AVAILABLE COLOURS

Transparency

This tape is suitable for the documents protection of a wide range of shipping parcels. The non tack adhesive areas avoid any damaging of the document enclosed. Hand or table dispenser application on the package. The printing and the non adhesive areas are customizable.



BACKING THICKNESS **28 µm**



PRINTED TAPE



BREAKING LOAD > 39 N/cm















PRINTED TAPES

INFORMATIVE DATA SHEET



	+		\(\)	jijk.	<i>></i>			•	9	*
	backing thickness µm	total thickness µm	adhesion N/cm	breaking Ioad N/cm	elongation at break %	available colours	medium weight packaging	light weight packaging	automatic sealing machine	suitable for low temperatures packaging
POLIPRINT 240	28	47	> 2,0	> 39	> 116	• 0 0		•	•	•
POLINARPRINT 260	32	51	> 2,0	> 45	> 116	• 0 0	•		•	•
POLINARPRINT 265	32	51	> 2,0	> 45	> 116	• • • •	•		•	•
NARPRINT 140	32	51	> 1,5 (BI) > 1,8 (AV TR)	> 45	> 48	• 0 0	•			
NARPRINT 165	37	56	> 1,8	> 50	> 48		•			
NARPOUCH 240	28	47	n.r.	> 39	> 116	Ø				
NARPOUCH 260	32	51	n.r.	> 45	> 116	Ø				
RENEWA® TAPE 465	58	135	> 2,2	> 31	> 7	• 0		•	•	

brown

O white

transparent

red

orange

black

yellow

green

light blue

blue

duo flu





NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product suitability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.

