



# NAR STRAP 520 BI

INFORMATIVE  
DATA SHEET



MADE IN ITALY

## HEAVY DUTY

### COMPOSITION

BACKING: monoaxially oriented polypropylene  
ADHESIVE: natural rubber / hydrocarbonic resins / solvent  
CORE: recycled paper and paperboard

### SUITABLE FOR

Heavy packaging; binding things; palletizing


### AVAILABLE COLOURS

White


The natural rubber adhesive, together with the high performances of the monoaxially oriented support, make this product particularly suitable for palletizing and stocking heavy and bulky packages.



HEAVY WEIGHT PACKAGING



TOTAL THICKNESS  
72  $\mu\text{m}$



BACKING THICKNESS  
50  $\mu\text{m}$



BREAKING LOAD  
> 160 N/cm



NAR S.P.A.  
Legnaro (PADOVA)  
ITALY  
[www.nar-spa.com](http://www.nar-spa.com)

Membro di:



LEGNARO - BRUGINE - SCHIO



LEGNARO










LEGNARO



# HEAVY DUTY

INFORMATIVE  
DATA SHEET



	 backing thickness µm	 total thickness µm	 adhesion N/cm	 breaking load N/cm	 elongation at break %	 heavy weight packaging	 available colours
NARFIL 500	28	120	> 8	> 220		•	⊗
NARGLASS 532	28	120	> 8	> 170		•	⊗
NARGLASS 539	28	130	> 8	> 220		•	⊗
NARSTRAP 520 AR / BI	50	72	> 2,4	> 160	> 27	•	● ○
NARSTRAP 540 NE	75	98	> 2,4	> 240	> 27	•	●

○ white    ⊗ transparent    ● orange    ● black



NAR S.P.A.  
Legnaro (PADOVA) ITALY  
[www.nar-spa.com](http://www.nar-spa.com)

It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product suitability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.



[www.nar-spa.com/  
technical-notes.html](http://www.nar-spa.com/technical-notes.html)