



NAR STRAP 540 NE

INFORMATIVE
DATA SHEET



MADE IN ITALY

HEAVY DUTY

COMPOSITION

BACKING: monoaxially oriented polypropylene
ADHESIVE: natural rubber / hydrocarbonic resins / solvent
CORE: recycled paper and paperboard


SUITABLE FOR

Heavy packaging; binding things; palletizing


AVAILABLE COLOURS

Black


The natural rubber adhesive, together with the high performances of the monoaxially oriented support, make this product particularly suitable for palletizing and stocking heavy and bulky packages.



TOTAL THICKNESS
98 μ m



BACKING THICKNESS
75 μ m



BREAKING LOAD
> 240 N/cm










HEAVY WEIGHT PACKAGING



HEAVY DUTY

INFORMATIVE
DATA SHEET



| |  backing thickness µm |  total thickness µm |  adhesion N/cm |  breaking load N/cm |  elongation at break % |  heavy weight packaging |  available colours |
|----------------------|---|--|---|--|--|--|---|
| NARFIL 500 | 28 | 120 | > 8 | > 220 | | • | ⊗ |
| NARGLASS 532 | 28 | 120 | > 8 | > 170 | | • | ⊗ |
| NARGLASS 539 | 28 | 130 | > 8 | > 220 | | • | ⊗ |
| NARSTRAP 520 AR / BI | 50 | 72 | > 2,4 | > 160 | > 27 | • | ● ○ |
| NARSTRAP 540 NE | 75 | 98 | > 2,4 | > 240 | > 27 | • | ● |

○ white ⊗ transparent ● orange ● black



NAR S.P.A.
Legnaro (PADOVA) ITALY
www.nar-spa.com

It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product suitability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.



[www.nar-spa.com/
technical-notes.html](http://www.nar-spa.com/technical-notes.html)