

INFORMATIVE DATA SHEET

				jij.							*	FSC FSC <sup>®</sup> C135011
	backing weight g/m²	total thickness µm	adhesion N/cm	breaking load Kg/5cm	elongation at break %	available colours	heavy weight packaging	medium weight packaging	light weight packaging	automatic sealing machine	easy cut	on request
ECOMASK® 460	58	135	> 2,2	> 15	>7	• 0			•	•	•	•
ECOMASK <sup>®</sup> HM 430	55	120	> 3,2	>14	> 8	•			•	•	•	•
RENEWA® TAPE 465	58	135	> 2,2	> 15	>7	• 0			•	•	•	•
NARKRAFT REINFORCED 490	105	200	n. r.	> 66	> 5	•	•			•		
ECOMASK <sup>®</sup> REINFORCED 460	58	190	> 2,2	> 20	> 5	•		•		•		•

● brown ○ white



NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product witability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.



www.nar-spa.com/ technical-notes.html

## ECOMASK® 460

INFORMATIVE DATA SHEET

### PAPER PACK

#### STRUCTURE

BACKING: lightly crepe paper ADHESIVE: natural rubber / hydrocarbonic resins CORE: recycled paper and paperboard

#### SUITABLE FOR

Light weight packaging, hand dispensers and automatic sealing machines

#### AVAILABLE COLOURS

Brown - white

Excellent grip after application. Particularly suited for light packaging by hand dispensers and automatic sealing machines applications.

In line with NAR's dedication to environmental sustainability, 65% of this product is made with materials from renewable resources.

It is suitable for printing on flexographic machines.



BACKING WEIGHT 58 g/m<sup>2</sup>



ADHESION > 2,2 N/cm



MATERIALS FROM RENEWABLE RESOURCES



NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com





DNV ISO 14001



LIGHT WEIGHT PACKAGING



AUTOMATIC SEALING MACHINE

ON REQUEST

## ECOMASK® HM 430

INFORMATIVE DATA SHEET



#### STRUCTURE

BACKING: lightly crepe paper ADHESIVE: synthetic rubber / hydrocarbonic resins CORE: recycled paper and paperboard

#### SUITABLE FOR

Light weight packaging, hand dispensers and automatic sealing machines

#### AVAILABLE COLOURS

Brown

NAR

Excellent grip after application. Particularly suited for light packaging by hand dispensers and automatic sealing machines applications. It is suitable for printing on flexographic machines.



BACKING WEIGHT 55 g/m<sup>2</sup>



ADHESION > 3,2 N/cm



BREAKING LOAD
> 14 Kg/5cm



LIGHT WEIGHT PACKAGING

ORGANIC SOLVENTS FREE

ON REQUEST

FSC<sup>®</sup> C135011

AUTOMATIC SEALING MACHINE

NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com







DNV



# RENEWA TAPE 465

INFORMATIVE DATA SHEET

### 20

BACKING: lightly crepe paper ADHESIVE: natural rubber / hydrocarbonic resins CORE: recycled paper and paperboard

PAPER PACK

#### SUITABLE FOR

STRUCTURE

Light weight packaging, hand dispensers and automatic sealing machines

#### AVAILABLE COLOURS

Brown - white

Excellent grip after application. Particularly suited for light packaging by hand dispensers and automatic sealing machines applications.

In line with NAR's dedication to environmental sustainability, 65% of this product is made with materials from renewable resources. The tape is printed with an exclusive NAR technology, which guarantees an excellent definition together with the affirmed performances of the natural rubber adhesive.



BACKING WEIGHT 58 g/m<sup>2</sup>



#### PRINTED TAPE



MATERIALS FROM RENEWABLE RESOURCES



LIGHT WEIGHT PACKAGING

ON REQUEST

FSC<sup>®</sup> C135011

AUTOMATIC SEALING MACHINE

NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com









MADE IN ITALY

### NARKRAFT REINFORCED 490



### PAPER PACK

#### STRUCTURE

BACKING: glass fiber reinforced kraft paper ADHESIVE: synthetic rubber / hydrocarbonic resins CORE: recycled paper and paperboard.

#### SUITABLE FOR

Heavy packaging; the stiffness of the backing permits an easy application also without hand dispensers

### AVAILABLE COLOURS

Brown

Self adhesive tape with siliconized fiberglass reinforced kraft paper backing. The high performance hot melt adhesive and the reinforced backing makes this product the ideal choice for the heaviest packaging needs. The particular adhesive formulation ensures an excellent tack on the cartons with consequent tamper evident characteristics. The stiffness of the backing permits the application also without hand dispensers.



BACKING WEIGHT 105 g/m<sup>2</sup>



BREAKING LOAD > 66 Kg/5cm

#### HEAVY WEIGHT PACKAGING

ORGANIC SOLVENTS FREE



NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com





DNV ISO 14001



## ECOMASK® REINFORCED 460



MEDIUM WEIGHT PACKAGING



FSC<sup>®</sup> C135011

PRINTABLE



PAPER PACK

#### STRUCTURE

BACKING: glass fiber reinforced kraft paper ADHESIVE: synthetic rubber / hydrocarbonic resins CORE: recycled paper and paperboard.

#### SUITABLE FOR

Medium weight packaging, hand dispensers and automatic sealing machines.

#### AVAILABLE COLOURS

Brown

Excellent grip after application and particularly suited for medium weight packaging. Thanks to the glass fibre reinforcement, the ECOMASK® REINFORCED 460 has a higher breaking load compared to the traditional products in lightly crepe paper. In line with NAR's dedication to environmental sustainability, this product is made with materials from renewable resources and is available, on request, with FSC® certification. It is suitable for printing on flexographic machines.



BACKING WEIGHT 58 g/m<sup>2</sup>



BREAKING LOAD > 20 Kg/5cm

REINFORCED



NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com





