



# POLI PRINT 240

INFORMATIVE  
DATA SHEET



LIGHT WEIGHT PACKAGING



AUTOMATIC SEALING MACHINE



SUITABLE FOR LOW TEMPERATURES PACKAGING

## PRINTED TAPES

### COMPOSITION

BACKING: printed or pre-printed biaxially oriented polypropylene film  
ADHESIVE: natural rubber / hydrocarbonic resins / solvent  
CORE: recycled paper and paperboard

### SUITABLE FOR

Hand dispensers and automatic sealing machines;  
sealing of recycled cardboard boxes

### AVAILABLE COLOURS

Brown - white - transparent

The quick adhesion at high and low temperatures on all cardboard, the resistance and brilliance typical of polypropylene films, make it ideal for all applications in the packaging sector.



BACKING THICKNESS  
28  $\mu$ m



BREAKING LOAD  
> 39 N/cm













PRINTED TAPE



# PRINTED TAPES

INFORMATIVE  
DATA SHEET



	 backing thickness µm	 total thickness µm	 adhesion N/cm	 breaking load N/cm	 elongation at break %	 available colours	 medium weight packaging	 light weight packaging	 automatic sealing machine	 suitable for low temperatures packaging
POLIPRINT 240	28	47	> 2,0	> 39	> 116	● ○ ⊘		•	•	•
POLINARPRINT 260	32	51	> 2,0	> 45	> 116	● ○ ⊘	•		•	•
POLINARPRINT 265	32	51	> 2,0	> 45	> 116	● ○ ⊘ ● ● ● ● ● ● ● ● ● ●	•		•	•
NARPRINT 140	32	51	> 1,5 (BI) > 1,8 (AV TR)	> 45	> 48	● ○ ⊘	•			
NARPRINT 165	37	56	> 1,8	> 50	> 48	● ● ● ● ● ● ● ● ● ● ● ● ● ●	•			
NARPOUCH 240	28	47	n.r.	> 39	> 116	⊘				
NARPOUCH 260	32	51	n.r.	> 45	> 116	⊘				
RENEWA® TAPE 465	58	135	> 2,2	> 31	> 7	● ○		•	•	

● brown   ○ white   ⊘ transparent   ● red   ● orange   ● black   ● yellow   ● green   ● light blue   ● blue   ● fluo orange



NAR S.P.A.  
Legnaro (PADOVA) ITALY  
[www.nar-spa.com](http://www.nar-spa.com)

It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it. The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product suitability to the specific condition of use. Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.



[www.nar-spa.com/  
technical-notes.html](http://www.nar-spa.com/technical-notes.html)